




ROCKY MOUNTAIN

Collection

FACING STONE
WITHOUT JOINT



CRSOL

ÉMOTIONS MINÉRALES

HUES



Natural**



Havana**



Shaded grey**



Anthracite**

* Non-contractual hues

** Chromatic variations (see overleaf)

PRODUCTS



Facing stone

L. 42 x h. 15
L. 42 x h. 15 (L)
L. 42 x h. 7.5
L. 21 x h. 7.5

Thickness 3 cm

and between 2 et 2,5 cm in the under-moulded version
Average weight : 46,4 kg/m²
and 40 kg/m² in an under-moulded version



Corner

L. 31 x l. 10 x h. 15/7,5
Thickness 3 cm



Lintel

L. 120 x l. 23.5 x h. 15
Thickness 3 cm

CHARACTERISTICS

- Panel facing stone, dry stone bar appearance
- Compatible for installation on ETI and lightweight siding
- Through-coloured
- Frost-resistant



CHROMATIC VARIATIONS

ORSOL products have varying degrees of shades from one hue to another. Refer to the following symbols for the degree of shade of each hue.



Example: the natural tone offers a richer degree of colour and patina (different shades from one stone to another) than the stone tone, which is more uniform. Variations in shade on a stone or from one stone to another inherent to the natural appearance of the products cannot be the subject of a complaint.

INSTALLATION OF FACING STONES

Download our [technical specifications](#) to identify your substrate, find out the authorised height of installation and for installation information. Only by complying with the recommendations described in this process will you be entitled to the ORSOL [10-year product guarantee](#).



TECHNICAL SPECIFICATIONS

Download the TECHNICAL SPECIFICATIONS at www.orsol.fr



Link to the document library: <https://www.orsol.fr/ressources/documenttheque>

PRECAUTIONS FOR USE

Check the conformity of the products and their packaging immediately upon receiving them, as complaints about the appearance of the products must be made before installation. Our liability is limited solely to the replacement of defective products (see our *General Terms and Conditions of Sale* available at www.orsol.fr).

In order to obtain a good aesthetic rendering, it is advisable to supply your sites in one go and to mix the contents of the different packages and pallets during their use; this mixture will reinforce the natural appearance of the products by harmonizing the colours and shades.

MAINTENANCE

Neomineral is a material of 99% mineral origin, which lives, breathes, and perspires according to its environment. To provide the facing stones with lasting protection, it is essential to **apply a water-repellent product** to limit the impact of external aggression. This treatment should be applied to a clean, dry product after installation, and may need to be **renewed every 5 years**.

Do not use high-pressure or steam cleaners, including all accessories (rotating nozzle, brush...) that may degrade the surface condition of the products.



CONSUMPTION OF INSTALLATION PRODUCTS

- **GLUE:** ORFLEX Hautes Performances: **7 to 8 kg/m²** indoors and **8 to 10 kg/m²** outdoors
- **PROTECTION:** Water-repellent (outdoors or in damp rooms): **9 m²/L**

*Information given for guidance only for the selected collection of facing stones.
For more details: www.orsol.fr*



BIT.LY/ORSOL-TUTO-POSE-PLAQUE

LAYOUT OF THE ROCKY MOUNTAIN COLLECTION



1 I install



2 I remove any excess adhesive



3 I apply the water-repellent

Layout = Way of arranging the facing stone elements to obtain a harmonious whole.



LAYOUT OF CORNERS:

- The corners must be installed before the facing stone. They must be glued at a rate of 1 lm per day.
- Glue the corners from bottom to top, swapping short and long sides from one row to the next and leaving a 2 mm joint between each corner.

PRODUCTION OF LINTELS:

- Lintels must be installed after quoins and before the facing.
- The lintels are longer than the dimensions of the door or window frame. They should protrude from 5 to 20 cm on each side of the frame (finished opening).
- To allow the passage of the lower part of the lintel, cut this part to the dimensions of the door or window frame.
- After bonding, support for 24 hours.

LAYOUT OF FACING STONES:



- Glue the panels horizontally, starting at the bottom of the wall and leaving a 2 mm gap between each panel while carefully adhering to the following instructions:
 - Avoid making aligned vertical joints more than 15 cm high (see diagram above)
 - Break horizontal lines every 1.5 lm maximum using all panel shapes.
 - Cross the panels at their middle (if possible) to avoid vertical joints.



TO ORDER

| | Reference | | | | Packaging | | Average weight (kg) | |
|--------------|-----------|--------|-------------|------------|---------------------------------------|---------------------------------------|---------------------|--------|
| | Natural | Havana | Shaded grey | Anthracite | Package | Pallet | Package | Pallet |
| Facing stone | RM5 | RM2 | RM8 | RM7 | 1 package (± 0,25 m ²) | 96 packages (± 24 m ²) | 12,50 | 1225 |
| Corner | ARM5 | ARM2 | ARM8 | ARM7 | 1 package (± 0,45 ml) | 48 packages | 9,20 | 458 |
| Lintel | LID5 | - | - | - | 1 unit | 12 units | 24,80 | 313 |

NOTE: We recommend that you supply the site all at once to ensure uniformity of the hues.